

# ACCUSPEC

## PACKAGING CORP.

Email: [accuspec@frontier.com](mailto:accuspec@frontier.com) Website: [accuspecpackaging.com](http://accuspecpackaging.com)  
 607-292-3010

**PRODUCT INFORMATION BULLETIN**  
**CADPAK CL**  
**TRANSPARENT HIGH BARRIER PACKAGING**  
**QPL MIL-PRF-22191F, Type 1, Class 1 (Unlimited Use)**

**Watervaporproof, Greaseproof, Flexible, Heat-Sealable**

**PHYSICAL PROPERTIES**

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	4.0	mil	ASTM D2103
Yield	6,300	in <sup>2</sup> /lb	Calculated
Puncture Resistance	21	lbs	FED STD 101
Tensile Strength MD/TD	37/28	lbs/in	ASTM D882
OTR	0.010	cc/100 in <sup>2</sup> /day @ 0% RH, 23°C	ASTM D3985
WVTR	0.003	g/100 in <sup>2</sup> /day @ 90% RH 40°C	ASTM F1249
Seal Strength	18	lbs/in	ASTM F88
Suggested Sealing Conditions	375°F, 40psi, 2.0sec		

*Disclaimer:* The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

**Accuspec Packaging Corporation**  
**4011 County Road 25 Dundee, NY 14837**  
 Email: [accuspec@frontier.com](mailto:accuspec@frontier.com) Website: [accuspecpackaging.com](http://accuspecpackaging.com)  
 607-292-3010